

CHANG CHUN PLASTICS CO., LTD.

NO. 301, SONGKIANG ROAD, 7TH FL., TAIPEI, 10477 TAIWAN
TEL : 886-2-2503-8131 (REF) FAX : 886-2-2501-8018

PBT 2000-201D Technical Data

Engineering Plastics Polybutylene Terephthalate

CCP PBT 2000-201D

PBT 2000-201D is a unreinforced flame-retarded injection molding grade.

Characteristics

- 1)Good UV resistant
- 2)excellent electrical property
- 3)excellent temperature resistance, high heat distortion temperature.
- 4)excellent mechanic and chemical property
- 5)excellent weatherability
- 6)excellent moldability
- 7)High resistance to fuels, oil, fats and many solvents

Injection Molding Condition

Cylinder temperatures	:	235-270°C
Nozzle temperature	:	250-270°C
Mould temperature	:	40-120°C, suitable temperature 60-80°C
Injection rate	:	middle - fast
Screw speed	:	60-120 rpm, to be chosen in such a way that plasticizing time is just within cooling time.
Pressure	Injection pressure	: 500-1200 kg/cm ²
	Holding pressure	: 300-800 kg/cm ²
	Back pressure	: 0-3 kg/cm ²
Mould shrinkage	Mould shrinkage 1.6 mm thickness horizon is 1.1-1.9% and vertical is 1.3-2.1% under the test method ISO 294.	

Packaging

25 kg/ paper bag, 850 kg/ PP super sack

Material handling

Moisture pick-up from ambient air should be avoided. Keep hopper properly closed.

CHANG CHUN PLASTICS CO., LTD.

NO. 301, SONGKIANG ROAD, 7TH FL., TAIPEI, 10477 TAIWAN
TEL : 886-2-2503-8131 (REF) FAX : 886-2-2501-8018

Engineering Plastics Polybutylene Terephthalate

CCP PBT 2000-201D

Property	Value	Unit	Test method
Density	1.45	g/cm ³	ISO 1183
Melting point	225	°C	DSC
Heat deflection temperature under load			
--- 1.80 Mpa	60	°C	ISO 75
--- 0.45 Mpa	160	°C	ISO 75
Flammability acc. to UL94, 0.8 mm thickness	V-0		UL 94
Tensile stress	60	MPa	ISO 527
Tensile strain	3.0	%	ISO 527
Flexural stress	100	MPa	ISO 178
Flexural modulus	2000	MPa	ISO 178
Charpy impact strength – notched, 23°C	2.5	KJ/m ²	ISO 179
Dielectric strength, 2 mm thickness	20	kV/mm	IEC 243
Volume resistivity	10 ¹⁴	Ω-cm	IEC 60093
Surface resistivity	10 ¹²	Ω	IEC 60093
Arc resistance	100	sec	UL 746A

* All data are the typical values of the material and not the minimum values of the material specifications.