

長春人造樹脂廠股份有限公司

台北市松江路三〇一號七樓

CHANG CHUN PLASTICS CO., LTD.

NO.301, SONGKIANG ROAD, 7TH FL.,
TAIPEI, 10477 TAIWAN

TEL:886-2-25001883

FAX:886-2-25018018

CCP PBT 4115-202F PROPERTIES

MATERIAL : PBT4115-202F(15%GF,WHITE)

VENDOR: CHANG CHUN PLASTICS CO., LTD.

TEST ITEM	TEST METHOD	UNIT	QC RANGE
比重 (SPECIFIC GRAVITY)	ASTM D-792		1.50-1.52
灰份 (ASH)		%	14-16
抗張強度 (TENSILE STRENGTH)	ASTM D-638	KG/CM ²	900-1100
伸長率 (ELONGATION)	CCP METHOD	%	4.0-5.5
抗折強度 (FLEXURAL STRENGTH)	ASTM D-790	KG/CM ²	1400-1800
抗折模數 (MODULUS)	ASTM D-790	KG/CM ²	45000-65000
衝擊強度 (IMPACT STRENGTH, NOTCHED)	ASTM D256	KG-CM/CM	5.0-7.5
熔融指數 (MELT INDEX)	ASTM D-1238	g/10MIN	17-23
耐燃等級	UL		1/32 INCH 94 V-0