

CHANG CHUN PLASTICS CO., LTD.

NO. 301, SONGKIANG ROAD, 7TH FL., TAIPEI, 10477 TAIWAN
TEL : 886-2-2503-8131 (REF) FAX : 886-2- 2501-8018

Engineering Plastics Polybutylene Terephthalate

PBT 4130-200K Technical Data

CCP PBT 4130-200K

PBT 4130-200K is a 30% glass fiber reinforced flame retarded injection molding grade.

Characteristics

- 1)excellent electrical property
- 2)excellent temperature resistance, high heat distortion temperature.
- 3)excellent mechanic and chemical property
- 4)excellent weatherability
- 5)excellent wear property
- 6)excellent moldability
- 7)High resistance to fuels, oil, fats and many solvents

Injection Molding Condition

Cylinder temperatures	: 235-270°C
Nozzle temperature	: 240-265°C
Mould temperature	: 40-120°C, suitable temperature 60-80°C
Injection rate	: middle - fast
Screw speed	: 60-120 rpm, to be chosen in such a way that plasticizing time is just within cooling time.
Pressure	Injection pressure : 500-1200 kg/cm ²
	Holding pressure : 300-800 kg/cm ²
	Back pressure : 0-3 kg/cm ²
Mould shrinkage	Mould shrinkage 1.6 mm thickness horizon is 0.1-0.5% and vertical is 0.6-1.4% under the test method ISO 294.

Packaging

25 kg/ paper bag.

Material Handling

Moisture pick-up from ambient air should be avoided. Keep hopper properly closed.

CHANG CHUN PLASTICS CO., LTD.

NO. 301, SONGKIANG ROAD, 7TH FL., TAIPEI, 10477 TAIWAN
TEL : 886-2-2503-8131 (REF) FAX : 886-2- 2501-8018

Engineering Plastics Polybutylene Terephthalate

CCP PBT 4130-200K

Property	Value	Unit	Method
Glass fiber content	30	%	
Density	1.61	g/cm ³	ISO 1183
Melt viscosity, 260°C, 1000sec ⁻¹	180	Pa*sec	ISO 11443
Melting point	225	°C	DSC
Heat deflection temperature under load			
--- 1.80 Mpa	200	°C	ISO 75
--- 0.45 Mpa	215	°C	ISO 75
Flammability acc. to UL94, 0.8 mm thickness	V-0		UL 94
Tensile stress	125	MPa	ISO 527
Tensile strain	2.6	%	ISO 527
Tensile modulus	11000	MPa	ISO 527
Flexural stress	185	MPa	ISO 178
Flexural modulus	8000	MPa	ISO 178
Charpy impact strength – notched, 23°C	9.0	KJ/m ²	ISO 179
Charpy impact strength – unnotched, 23°C	55	KJ/m ²	ISO 179
Izod impact strength – notched, 23°C	8.5	KJ/m ²	ISO 180
Izod impact strength – unnotched, 23°C	40	KJ/m ²	ISO 180
Dielectric strength, 2 mm thickness	20	KV/mm	IEC 60243
Volume resistivity	10 ¹⁵	Ω-cm	IEC 60093
Surface resistivity	10 ¹²	Ω	IEC 60093
Arc resistance	90	sec	UL 746A

* All data are the typical values of the material and not the minimum values of the material specifications.