

Stanyl® TS200F6

PA46-GF30

30% Glass Reinforced

Print Date: 2017-11-03

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage [parallel]	0.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.3 / *	%	Sim. to ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	10000 / 6000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	5500	MPa	ISO 527-1/-2
Tensile modulus (160°C)	5000	MPa	ISO 527-1/-2
Tensile modulus (180°C)	4400	MPa	ISO 527-1/-2
Tensile modulus (200°C)	4000	MPa	ISO 527-1/-2
Stress at break	210 / 115	MPa	ISO 527-1/-2
Stress at break (120°C)	110	MPa	ISO 527-1/-2
Stress at break (160°C)	100	MPa	ISO 527-1/-2
Stress at break (180°C)	95	MPa	ISO 527-1/-2
Stress at break (200°C)	90	MPa	ISO 527-1/-2
Strain at break	4 / 7	%	ISO 527-1/-2
Strain at break (120°C)	7.5	%	ISO 527-1/-2
Strain at break (160°C)	7.5	%	ISO 527-1/-2
Strain at break (180°C)	7.5	%	ISO 527-1/-2
Strain at break (200°C)	7.5	%	ISO 527-1/-2
Flexural modulus	9000 / 5500	MPa	ISO 178
Flexural modulus (120°C)	4700	MPa	ISO 178
Flexural modulus (160°C)	3900	MPa	ISO 178
Charpy impact strength (+23°C)	80 / 100	kJ/m ²	ISO 179/1eU

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Properties	Typical Data	Unit	Test Method
Charpy impact strength (-30°C)	65 / 75	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 21	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	11 / 11	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	12 / 21	kJ/m ²	ISO 180/1A
Izod notched impact strength (-40°C)	11 / 11	kJ/m ²	ISO 180/1A

Thermal properties

dry / cond

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Burning Beh. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Burning Beh. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.83 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Relative Temperature Index - electrical	65	°C	UL746B
RTI electrical (Thickness (1) tested)	0.83	mm	UL746B
Thermal Index 5000 hrs	152	°C	IEC 60216/ISO 527-1/-2

Electrical properties

dry / cond

Volume resistivity	1E13 / 1E9	Ohm*m	IEC 60093
Electric strength	35 / 25	kV/mm	IEC 60243-1
Comparative tracking index	500 / -	V	IEC 60112
Relative permittivity (100Hz)	4.4 / 12	-	IEC 60250
Relative permittivity (1 MHz)	4 / 4.6	-	IEC 60250

Other properties

dry / cond

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

Property Data

Stanyl[®] TS200F6

Print Date: 2017-11-03

Properties	Typical Data	Unit	Test Method
Humidity absorption	2.6 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.