

Typical properties of Xydar[®] HM-402 BH

Properties	Unit	Method (ASTM)	HM-402 BH
Tensile strength (抗拉强度) (3.2mmT)	MPa	D638	129
Tensile Modulus (抗拉弹性率) (3.2mmT)	GPa		19.3
Elongation (抗拉伸率) (3.2mmT)	%		2.0
Flexural strength (弯曲强度) (3.2mmT)	MPa	D790	162
Flexural modulus (弯曲弹性率) (3.2mmT)	GPa		15.7
Poisson's ratio(泊松比)	—	—	0.46
Izod impact strength (un-notched)	kJ/m ²	D256	52
Rockwell hardness	R scale	D785	105
Specific gravity (比重)	—	D792	1.70
Water absorption(吸水率)	%	D570	0.02
Deflection temperature under load (熱変形温度) (load 1.82MPa)	degree C	D648	313
Thermal conductivity(熱伝導率)	kcal/m·hr·°C	F433	0.241
Flammability rating (難燃性) (V-0 applied thickness)	mm	UL94	0.18
Oxygen index(酸素指数)	%	D2863	45
Dielectric strength(耐電強度)	KV/mm	D149	35.4
Arc resistance(帯電弧)	sec	D495	123
Volume resistivity (体積抵抗率)	×10 ¹⁵ Ω·cm	D257	24.4
Surface resistivity(表面抵抗率)	×10 ¹⁵ Ω		22.6
Dielectric constant (介電常数)	10 ² Hz	D150	4.2
	10 ⁶ Hz		3.7
Dielectric dissipation factor (介質損耗角正切)	10 ² Hz	D150	NA
	10 ⁶ Hz		0.028

XYDAR[®] is a trademark of Solvay Advanced Polymers, L.L.C.



Coefficient of Linear Thermal Expansion & Molding Shrinkage
 (線膨張係数 & 成形収縮率)

Grade	Direction	Coefficient of Linear Thermal Expansion (Unit: 10^{-5} cm/cm/°C)					Molding Shrinkage (Unit: %)
		Temperature (°C)					
		50-100	100-150	150-200	200-250	250-300	
HM-402 BH	MD	0.3	0.3	0.0	-0.1	-0.5	0.00
	TD	3.8	4.2	5.3	5.7	5.7	0.75

Direction: MD = Machine Direction(縦方向)

TD = Transversal Direction(横方向)

Molding Conditions(成形条件)

		Unit	Conditions
Cylinder Temperature(料筒温度)	Rear(後)	°C	320~350
	Middle(中)	°C	340~370
	Front(前)	°C	370~390
Nozzle Temperature(噴嘴温度)		°C	370~390
Mold Temperature(模具温度)		°C	60~150
Injection Pressure(射出压力)		MPa	40~120
Injection Speed(射出速度)		-	Mid ~ High
Drying Condition(干燥条件)		°C	Over 150
		Hrs	4~24

Remark)

* Please apply Drying @150°C over 4 hours. This procedure is definitely necessary in order to prevent decay of material.