

Property	Test Condition	Test Method ISO	Units	GF reinforced
				GF40%, Standard
				A504X90
				>PPS-GF40<
Physical property				
Water Absorption	24hrs. in 23°C water	ISO62	%	0.02
Density	23°C	ISO1183	kg/m ³	1660
Color				Natural/Black
Mechanical property				
Tensile strength	23°C	ISO527-1,2	MPa	200
Elongation at Break	23°C	ISO527-1,2	%	1.8
Flexural Strength	23°C	ISO178	MPa	305
Flexural Modulus	23°C	ISO178	GPa	15.5
Coefficient of friction	Vs metal	-	-	0.25
Shear Strength	23°C	JIS K7214	MPa	80
Rockwell Hardness		ISO2039-2	R Scale	122
Taper Abrasion		ISO9352	mg/1000times	50
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m ²	11
Charpy Impact Strength (Unnotched)	23°C	ISO179	kJ/m ²	55
Heat property				
Melting Point		ISO11357-3	°C	278
Coef of Linear Thermal Expansion	Machine Direction	ISO11359-2	×10 ⁻⁵ /K	2.3
Coef of Linear Thermal Expansion	Transverse Direction	ISO11359-2	×10 ⁻⁵ /K	3.1
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	°C	260
Flammability		UL94	rank/thickness m mt	V-0 (0.28mmt)
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹⁴
Dielectric Strength		IEC60243-1	MV/m	24
Dielectric Constant	23°C, 60%RH, 1MHz	IEC 60250	-	4.2
Dissipation Factor	23°C, 60%RH, 1MHz	IEC 60250	-	0.002
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.2
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.8
Bar Flow	320°C,98MPa,1mmt	Toray Method	×10 ⁻³ m	135

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.